



Wrapping Grade Laminate Décor Performance

Applications:
Mouldings

JUNE 2016

Resistance	Description	Standard	Typical Values
Wear	Measure of the ability of the surface to keep its design or color under abrasive wear	NEMA LD3-2005	Solid: 400 cycles Print: 125 cycles
Stain	Measure of the ability of the decorative surface to resist to stain when exposed to 15 household products	NEMA LD3-2005	1-14 No effect 15 Slight
Cleanability	Measure of the ability of a decorative surface to be cleaned when exposed to 15 soiling agents	NEMA LD3-2005	No effect
Light Resistance	Measure of the ability of a decorative surface retain it color when exposed to a light source close to the sunlight	NEMA LD3-2005	Slight
High Temperature	Measure of the ability of a decorative surface to maintain its color and aspect when exposed to high temperatures	NEMA LD3-2005	Slight
Radiant Heat	Measure of the ability of a decorative surface to resist any damage when exposed to a radiant heat source	NEMA LD3-2005	No effect
Boiling Water	Measure of the ability of a decorative surface to resist any damage when exposed to boiling water for 20 minutes.	NEMA LD3-2005	No effect
Impact	Measure of the maximal falling height of a steel ball that does not cause fracture to the decorative surface	NEMA LD3-2005	24"

The above information is to help in selecting suitable products for their applications. We request that our customers inspect and test our laminate before use and satisfy themselves as to the specifications and suitability.